

Amendments to the Claims:

1. (Previously presented) A heat-sensitive stencil master comprising a heat-sensitive polymeric film having a thickness of less than 10  $\mu\text{m}$  and, coated thereon, a solid foam comprising a cross-linked resin and a foaming agent.

2. (Original) A stencil master according to claim 1, wherein the foaming agent is a surfactant having an HLB of greater than 6.

3. (Original) A stencil master according to claim 1, wherein the solid foam incorporates a fibrous material.

4. (Original) A stencil master according to claim 3, wherein the fibrous material has a diameter of greater than 1  $\mu\text{m}$  and less than 10  $\mu\text{m}$ , and a length in the range of 100  $\mu\text{m}$  to 14 mm.

5. (Original) A stencil master according to claim 3, wherein the fibrous material has a length in the range of 100  $\mu\text{m}$  to 500  $\mu\text{m}$ .

6. (Previously presented) A stencil master according to claim 3, wherein the fibrous material is selected from the group consisting of carbon fibres, glass fibres, and polymeric fibres.

7. (Original) A stencil master according to claim 6, wherein the fibrous material comprises carbon fibres.

8. - 9. (Canceled)

10. (Previously presented) A stencil master according to claim 1, wherein the resin is cross-linked by irradiation.

11. (Previously presented) A stencil master according to claim 1, wherein the resin is cross-linked by electron beam irradiation.

12. (Previously presented) A stencil master according to claim 1, wherein the resin is a polyurethane cross-linked through unsaturated acrylate groups.

13. (Original) A stencil master according to claim 1, wherein the solid foam incorporates an antistatic agent.

14. (Original) A stencil master according to claim 1, wherein the heat-sensitive polymeric film has a release coating on the side of the film opposite the solid foam.

15. (Original) A stencil master according to claim 1, wherein the foaming agent comprises ammonium stearate, a sulphate foaming agent or a mixture thereof.

16. (Canceled)

17. (Original) A stencil for use in a digital duplicating printing process comprising a stencil master as defined in claim 1, which has been thermally imaged to produce voids in the heat-sensitive polymeric film.

18. (Canceled)

19. (Previously presented) A heat-sensitive stencil master comprising a heat-sensitive polymeric film and, coated thereon, a solid porous coating comprising a cross-linked resin and having a filler dispersed therein, wherein the filler is selected from the group consisting of carbon fibres, carbon particles and mixtures thereof.

20. (Original) A stencil master according to claim 19, wherein the filler comprises carbon fibres having a diameter of greater than 1  $\mu\text{m}$  and less than 10  $\mu\text{m}$ , and a length in the range of 100  $\mu\text{m}$  to 14 mm.

21. (Original) A stencil master according to claim 20, wherein the carbon fibres have a length in the range of 100  $\mu\text{m}$  to 500  $\mu\text{m}$ .

22. - 23. (Canceled)

24. (Previously presented) A stencil master according to claim 19, wherein the resin is cross-linked by electron beam irradiation.

25. (Canceled)

26. (Original) A stencil for use in a digital duplicating printing process comprising a stencil master as defined in claim 19, which has been thermally imaged to produce voids in the heat-sensitive polymeric film.

27 – 30. (Cancelled)

31. (Previously presented) A stencil master according to claim 6, wherein the polymeric fibres are selected from the group consisting of polyester fibres and polyvinyl alcohol fibres.

32. (Previously presented) A stencil master according to claim 1, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g}/\text{m}^2$ ) ratio of at least 6.

33. (Previously presented) A stencil master according to claim 1, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g}/\text{m}^2$ ) ratio of at least 8.

34. (Previously presented) A stencil master according to claim 1, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g/m}^2$ ) ratio of at least 10.

35. (Previously presented) A stencil master according to claim 19, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g/m}^2$ ) ratio of at least 6.

36. (Previously presented) A stencil master according to claim 19, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g/m}^2$ ) ratio of at least 8.

37. (Previously presented) A stencil master according to claim 19, wherein the stencil master has a stiffness (mN):coating weight ( $\text{g/m}^2$ ) ratio of at least 10.